

TECHNICAL PROPERTIES

PROPERTY	METHOD	MAMMUT
Raw material		European bull hides
Brand mark		No brand marks
Hump		No hump
Average substance		0,9-1,3 mm
Average size		Ca 5m2
Dyeing		FOC drum-through dyed
Grain		Corrected embossed grain
Tensile strength	DIN EN ISO 3376	>80 N
Fastness to rubbing	EN ISO 11640	>dry 500 >wet 80 >pH8 50 Felt: >4 GS Finish: >4 GS No damage of finish
Tear resistance	DIN EN ISO 3377-1	>20 N
Adhesion of finish after 30000 FLEX	ISO 11644 / DIN EN ISO 5402	>2,5 N/cm
PH-value	DIN ISO 4045	>3,5
Flexometer test	DIN EN ISO 5402	>30.000 cycles
FLAMMABILITY		
Combustibility	IMO-Res. A 652 (16) ÖNORM B3825 hardly inflammable DIN 5510-2 Papierkissen-test BS 5852 Crib7	Passed Passed (with a special finish) Passed (with a special finish) Passed (with a special finish)
Smoke density	ÖNORM B3800	Passed Q1
Dripping	ÖNORM B3800	Passed TR1
Flammability	BS 5852 Crib5	Passed
Cigarette/match-test	EN 1021 1+2	Passed
Reach	Free of harmful substances	Passed
Der Blaue Engel	Environmental friendly	Passed
ISO 14001	Environmental management	Passed
ISO 9001:2008	Quality management	Passed

